



REC'D PCT/PTO

07 FEB 2005

GB 03 / 3459



#2

INVESTOR IN PEOPLE

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

The Patent Office
Concept House

Cardiff Road

Newport

South Wales

NP10 9BQ

03 SEP 2003


PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Andrew Gersey

Dated

20 August 2003

BEST AVAILABLE COPY




08AUG02 173946541 D00355
F01/7700 0.00-0218382.0

1/77

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)



The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1. Your reference

W071491PGB

2. Patent application number

(The Patent Office will fill in this part)

0218382.0

8 AUG 2002

3. Full name, address and postcode of the or of each applicant (underline all surnames)

The University of Birmingham
Edgbaston
Birmingham
B15 2TT

Patents ADP number (if you know it)

798165002

If the applicant is a corporate body, give the country/state of its incorporation

England

4. Title of the invention

IMPROVED INVESTMENT CASTING PROCESS

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Marks & Clerk
Alpha Tower
Suffolk Street Queensway
Birmingham, B1 1TT
England

Patents ADP number (if you know it)

18002

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

YES

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description 9

Claim(s)

Abstract

Drawing(s) 1  

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)


Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature



Date

7/8/02

12. Name and daytime telephone number of person to contact in the United Kingdom

David I. WARD 0121 643 5881

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

IMPROVED INVESTMENT CASTING PROCESS

The present invention relates to an improved investment casting process, and in particular to a process which is much more rapid than conventional processes.

A typical investment casting process involves the production of engineering metal castings using an expendable pattern. The pattern is a complex blend of resin, filler and wax which is injected into a metal die under pressure. Several such patterns, once solidified are assembled into a cluster and mounted onto a wax runner system. The wax assembly is dipped into a refractory slurry consisting of a liquid binder and a refractory powder. After draining, grains of refractory stucco are deposited onto the damp surface to produce the primary refractory coating (the covering of the assembly with refractory material is known as "investing", hence the name for the process). When the primary coat has set (usually by air drying until the binder gels) the assembly is repeatedly dipped into a slurry and then stuccoed until the required thickness of mould shell is built up. Each coat is thoroughly hardened between dippings, and so each mould can take from between 24 and 72 hours to prepare. The purpose of the stucco is to minimise drying stresses in the coatings by presenting a number of distributed stress concentration centres which reduce the magnitude of any local stresses. Each stucco surface also provides a rough surface for keying in the next coating. The particle size of the stucco is increased as more coats are added to maintain maximum mould permeability and to provide bulk to the mould.

In recent years, advanced ceramics (eg. silicon nitride) components have been developed which offer significant advantages over comparable metal components. Many processes by which such ceramic components can be made are known, and these include machining, injection moulding, slip casting, pressure casting and gelcasting. In gelcasting, a concentrated slurry of ceramic powder in a solution of organic monomer is poured into a mould and polymerised in situ to form a green body in the shape of the mould cavity. After demoulding, the green ceramic body is dried, machined if necessary, pyrolysed to remove binder and then sintered to full density. Aqueous based systems, such as the acrylamide system, have been developed in which water-soluble monomers are used, with water as the solvent.

It is an object of the present invention to provide an improved investment casting process which obviates or mitigates one or more problems associated with known investment casting processes and which preferably significantly reduces the time required for forming a shell mould.

According to the present invention, there is provided a process for the production of a shell mould, comprising the sequential steps of:-

(i) dipping a preformed expendable pattern into a slurry of refractory particles and liquid binder whereby to form a coating layer on said pattern,

(ii) depositing particles of refractory material onto said coating, and

(iii) drying,

steps (i) to (iii) being repeated as often as required to produce a shell mould having the required number of coating layers, characterised in that during at least one performance of step (ii) particles of a gel-forming

material are also deposited onto the coating layer formed in step (i) such that after contact with the coating layer moisture is absorbed by the gel forming material thereby causing gellation of the binder so reducing the time required for drying in step (iii).

Preferably, the method also includes the additional step (iv), carried out after step (iii) of applying a seal coat comprising a slurry of refractory particles and liquid binder, followed by drying.

In shell mould formation, the coating layer applied to the expendable pattern is usually referred to as the primary coating and subsequent slurry coatings are referred to as secondary coatings.

Preferably, the gel-forming material is applied onto each secondary coating (i.e. during each repetition of step (ii) after the first).

Preferably, said gel-forming material is a polymer, more preferably a super absorbent polymer exemplified by polyacrylamide and polyacrylate.

The desirable particle size for the polymer will be related to the size of the particles of the refractory material. In general, at least 50wt% (and even more preferably at least 80wt%) of the polymer particles are preferably no larger than 1.5 mm and more preferably no larger than 1 mm. Preferably, at least 50wt% (and even more preferably at least 80wt%) of polymer particles are larger than 150 μm and more preferably larger than 300 μm . In a particularly preferred embodiment, substantially all (i.e. at least 95wt%) of the polymer particles are from 300 μm to 1 mm in size.

Advantageously, the process (apart from the use of the moisture absorbing material and the reduced drying times which result) is substantially the same as a standard investment casting process using conventional machinery and materials. Thus, it will be understood that the nature of the expendable pattern, the slurry compositions used in step (i) (and step (iv) when present) and the refractory particles used in step (ii) may be any of those known to the person skilled in the art of investment casting.

Moreover, the method preferably includes a step of removing the expendable pattern from the shell mould after the last step (iii) and more preferably the method includes a final step of firing the resultant shell mould.

The present invention further resides in a shell mould producible by the method of the present invention.

The present invention will be further described by way of example only with reference to the accompanying drawing which is a cross-sectional view of a shell mould made in accordance with the method of the present invention.

Comparative Example 1

The comparative example was intended to be representative of a standard shell used for aluminium alloy casting and was constructed as follows:-

A filled-wax test piece was dipped into a first slurry (primary) for 30 seconds and drained for 60 seconds. Coarse-grained stucco material was

then deposited onto the wet slurry surface. The coated test piece was placed on a drying carousel and dried for the required time under controlled conditions of low air movement. Extended drying removes moisture from the colloidal binder, forcing gellation of the particles to form a rigid gel.

Subsequent coats were applied by dipping (30 seconds) in a second (secondary) slurry followed by draining (60 seconds), with subsequent stucco application and drying for the required time after each stucco application. In total, three secondary coatings were applied. Finally, a seal coat was applied (dip in secondary slurry, but no stucco application), followed by drying.

The primary and secondary slurry specifications are contained in Table 1, with the other various process parameters being given in Table 2. The latex addition in Table 1 relates to the use of a water-based latex system which is added to the base binder to improve unfired strength.

Table 1: Slurry specifications for aluminium shell preparation
(all figures are wt %)

Slurry	binder silica content (wt%)	latex polymer addition (wt%)	filler type	refractory loading (wt% of total slurry)
Primary	26	6	(a) 200 mesh zircon (b) 200 mesh fused silica	80% a:b 3:1
Secondary	22	8	200 mesh aluminosilicate	57%

Table 2: Shell build specifications for comparative example

Coating	Stucco	Drying air speed (ms ⁻¹)	Drying time (mins)
primary	50/80 mesh alumino-silicate	0.4	1440
secondary 1	30/80 mesh alumino-silicate	3	90
secondary 2	30/80 mesh alumino-silicate	3	90
secondary 3	30/80 mesh alumino-silicate	3	90
secondary 4	30/80 mesh alumino-silicate	3	90
seal coat	none	3	1440
		Total	3240

Example 1

The shell mould according to Example 1 was made in the same manner as for the comparative example using the slurries of Table 1, except that the stucco applied onto the secondary coatings included particles of polyacrylamide at a loading of 1 part polyacrylamide to 10 parts stucco. The process parameters are given in Table 3. When the polyacrylamide is deposited onto the wet slurry surface, it rapidly absorbs moisture from the adjacent colloidal portion of the slurry forcing gellation to a rigid gel without the necessity of extended drying times.

It is anticipated that drying times can be reduced even further by the inclusion of polyacrylamide polymer in the stucco applied to the primary slurry coating.

Table 3: Shell build specifications for Example 1

Coating	Stucco	Drying air speed (ms ⁻¹)	Drying time (mins)
primary	50/80 mesh alumino-silicate	0.4	1440
secondary 1	30/80 mesh alumino-silicate -polyacrylamide* (10:1)	3	10
secondary 2	30/80 mesh alumino-silicate -polyacrylamide* (10:1)	3	10
secondary 3	30/80 mesh alumino-silicate -polyacrylamide* (10:1)	3	10
secondary 4	30/80 mesh alumino-silicate -polyacrylamide* (10:1)	3	10
seal coat	none	3	10
		Total	1490

* particle size 86wt% > 1mm, 500µm ≤ 14wt% ≤ 1mm

The shell mould produced in accordance with the method of the present invention is shown in the drawing. The shell is less dense and uniform in comparison with the comparative example (not shown). The shell of Example 1 is more open and delaminated in places due to swelling of the individual polymer particles during absorbance of moisture from the colloidal binder. The large particle size is disadvantageous in this respect and it is anticipated that these defects will be much reduced by the use of a smaller and much more controlled particle size polyacrylamide addition to the standard stucco sizes.

Shell Thickness Comparisons

Comparisons of the ceramic shell thickness achieved for acrylamide modified (Example 1) and standard (comparative example) shell systems can be seen in Table 4. The polyacrylamide increases the shell thickness because the particle size is much larger than the stucco itself. The large

size is also represented by the relatively large standard deviation in the data.

Table 4: shell thickness comparison

	status	No. of samples	Average Thickness (mm)	standard deviation (mm)
Example 1	unfired	10	4.60	0.26
Comparative Example	unfired	5	6.81	0.92

Room Temperature Flat Bar Strength Measurement

Strength measurements were carried out in accordance with BS 1902. Injected wax bars were used as the formers for the ceramic shells formed by the procedures indicated above. After formation, the shells were steam Boilerclave (TM) de-waxed at 8 bar pressure for 4 minutes, followed by a controlled de-pressurisation cycle at 1 bar/minute. Test pieces, approximately 20mm x 80mm were cut using a grinding wheel and tested in a 3 point bend mode at room temperature.


A comparison of the maximum strengths achieved at room temperature in the 3-point bend mode for the shell samples is shown in Table 5. The high dry, green strength of the comparative example shell is a direct result of the latex polymer content, which is reflected by the reduction in strength as the sample is fired at 1000°C and the latex burns out (data not shown). The strength of the Example 1 shell is relatively low, which is a direct result of the delamination and defects introduced by the use of a very large particle size polyacrylamide. It is anticipated that by the use of a matched stucco size, the swelling of the acrylamide polymer should be

reduced to a level which would be more acceptable for investment casting.

Table 5: flat bar fracture strength

Sample	test piece	status	fracture strength
Comparative Example 1	flat bar	green, dry	7.8 +/-0.7
Example 1	flat bar	green, dry	2.2 +/-0.9

v/1



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.